

Liqui-Cel®

MEMBRANE CONTACTORS

Chemical Resistance Guidelines for Liqui-Cel®, SuperPhobic®,
MiniModule™, and MicroModule™ Contactors

www.liqui-cel.com



MEMBRANA
Now proudly part of 3M

CHEMICAL RESISTANCE TABLE

The Chemical Resistance Table below is an informational guide for the use of various chemicals with components used in 3M Membrane Contactors. The contents of this table are the general chemical resistance characteristics of the raw materials for the contactor components. The table is a general guide only and should not be considered as a substitute for testing under your specific conditions.

Chemical Resistance Classification	
S	Satisfactory. No or very little chemical influence on performance
L	Limited Resistance. Exposure time must be limited to maintain adequate performance
U	Unsatisfactory. Adequate performance not possible with this chemical
	Blank. Chemical is Untested

Chemical Resistance Summary														
	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Water & Aqueous Solutions	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Bases	S	U	S	S	S	S	S	S	S	L	L	L	S	S
Acids-Dilute	L	L	S	S	S		S	S	S	U	S	L	S	S
Acids-Strong	U	U	L	L	L		U	S	U	U	L	L	S	L
Halogens	U	U	U	U	U		U	S	U	U	L	L	S	U
Aliphatic Hydrocarbons	S	L	L	L	L		U	S	L	S	L	S	S	U
Alicyclic Hydrocarbons	S	L	L	L	L		U	L	U	L	L	S	S	U
Aromatic Hydrocarbons	L	L	L	L	L		U	S	U	S	U	S	S	U
Heterocyclic Compounds	L	U	L	L	L			L	U	L	L	L	S	U
Amines	L	U	L	L	L		U	U	U	L	U	U	S	L
Alcohols	S	U	S	S	S	S	U	S	L	S	S	L	S	S
Glycols & Glycerols	S	U	S	S	S		L	S	S	S	L	L	S	S
Aldehydes	L	U	L	L	L		U	U	L	S	L	L	S	L
Ketones	L	U	S	S	S		U	U	U	S	U	U	S	L
Anhydrides	U	U	S	S	S			U	U	S	U	U	S	
Halogenated Hydrocarbons	L	U	U	U	U		U	L	U	L	U	L	L	U
Esters	L	U	S	L	L		U	L	U	S	U	U	S	L
Phenolics	L	L	S	S	S		U	L	L	U	U	U	S	L

Chemical Resistance Table														
	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Acetaldehyde	U	U	L	L	L	S	U	U	U	S	L	U	S	L
Acetic Acid (10%)	L	L	S	S	S	S	L	S	U	U	S	L	S	S
Acetic Acid (Glacial)	U	U	S	S	S	S	U	L	U	S	S	U	S	L
Acetic Anhydride	U	U	S	S	S	S	U	U	U	S	U	U	S	L
Acetone	L	U	S	S	S	S	U	U	U	S	U	U	S	S
Acetonitrile	U	U	S	S	L	S		L	U	S	U	U	S	S
Acetophenone	U	U	S	S	L		U	U	U	S	U	U	S	S
Acetyl Chloride	U	U	L	U		S	U	L	L	S		S	S	U
Acrylic Acid140	U	U	S	L				S				U	S	L
Aluminum Chloride (10%)	S	L	S	S	S	U	S	S	S	U	S	S	S	S
Aluminum Sulphate	S	L	S	S	S	L	S	S	S	S	S	S	S	S
Ammonium Hydroxide (35%)	L	U	S	S	S	S	S	S	S	S	S	L	S	S

PO = Polyolefin in SuperPhobic Products
 PC = Polycarbonate
 PU = Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Ammonium Sulphate (50%)	S	L	S	S	S	S	S	S	S	S	S	S	S	S
Amyl Acetate	L	U	S	L	L	S	U	L	U	S	U	U	S	S
Amyl Alcohol	S	U	S	L	L	S	S	L	S	S	S	L	S	S
Aniline	U	U	S	S	L	S	U	L	L	S	U	S	S	L
Antimony Trichloride (10%)	S	S	S	S		U	S		S	U	S	S	S	
Aqua Regia	U	U	U	U	U	U	U	L	L	U	U	L	S	L
Arsenic Acid	L	L	S	S	S	S	S	S	S	L	S	S	S	S
ASTM OIL #1	S	L	S	S								S	S	U
ASTM OIL #2	S	L	S	L								S	S	U
ASTM OIL #3	S	L	S	L								S	S	U
Barium Chloride	S	S	S	S		S	S	S	S	S	S	S	S	S
Benzaldehyde	U	U	S	U	L	S	S	L	U	S	U	U	S	S
Benzene	S	U	L	U	U	S	U	S	L	S	U	S	S	U
Benzyl Alcohol	U	U	S	S	S		U	S	L	U	U	S	S	L
Benzyl Chloride	U	U	L	L		S	U	S		S	U	S	S	U
Boric Acid	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Bromine	U	U	U	U	U	U	U	S	L	U	L	S	S	U
Butyl Acetate	L	U	S	L	L	S	U	L	U	S	U	U	S	L
Butyl Alcohol (Butanol)	S	U	S	S	S	S	U	S	L	S	S	L	S	L
Butyl Amine	L	U		L			U	U	U	S	U	U	S	U
Butyric Acid	U	U	L	S	U	S	U	S	S	L	U	S	S	L
Butyl Chloride	S	U	U	U	L		U	S	L	S	S	L	S	
Calcium Chloride	S	S	S	S	S	S	S	S	L	S		S	S	S
Carbon Disulphide	S	U	U	U	U	S	U	L	U			S	S	U
Carbon Tetrachloride	S	U	U	U	U	S	U	S	U	U	U	S	L	U
Castor Oil	S	S	S	S			S	S				S	S	L
Cello-Solve Glycol Ether	U	U										S	S	
Cello-Solve Acetate	U	U	S	S	S		U	S	L	S	L	U	S	L
Chloroacetic Acid	U	U	S	L	S	S		U	S	U	U	U	S	L
Chlorobenzene	U	U	L	U	U	S	U	S	U	U	U	S	S	U
Chlorine Dioxide	U	U			U			S				S	S	L
Chlorine Gas	L	U	L	U	L	S		S	U	U	L	S	S	U
Chlorine (Water)	L	L	L	U	U	L	U	S	S	L	L	S	S	L
Chloroform	U	U	L	U	U	S	U	L	U	S	U	S	S	U
Chlorosulphuric Acid	U	U	U	U								U	S	
Chrome Plating Solutions	U	U	S	L								S	S	L
Chromic Acid	U	U	S	L	L	S	L	L	S	U	U	S	S	L
Citric Acid (10%)	S	S	S	S	S	S	S	S	S	S	S	S	S	S
COD Liver Oil	L	L	S	S								S	S	S
Copper Sulphate	S	S	S	S	S	S	S	S	S	U	S	S	S	S
Cottonseed Oil	S	S	S	S				S	S	S		S	S	L
Cresols	U	U	L	L	U	S	U	S	U	U	U	S	S	U
Cyclohexane	S	S	L	L	U	S	U	S	U	S	S	S	S	U
Cyclohexanol	S	L	S	L	S		U	S	U	L	L	S	S	U
Cyclohexanone	S	L	S	U	L	S	U	L	U	S	U	U	S	L
Decahydronaphthalene	L	U	L	U	L				S	S	S	S	S	U
Diesel	S	L	L	L		S		S	S	S	S	S	S	U
Diethylamine	U	U	L	L	L	S	U	L	U	S		S	S	L
Diethylene Glycol	S	U	S	S	S	S	S	S	L	S	L	S	S	S
Diethyl Ether	L	U	L	L	U	S	U	S	U	S	U	U	S	U

PO = Polyolefin in SuperPhobic Products
 PC = Polycarbonate
 PU = Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Dimethyl Formamide	U	U	S	S	S	S	U	U	U	S	U	U	S	L
Dimethyl Hydrazine	U	U	S	S								U	S	
Dimethylamine	U	U	S	L				L			U	U	S	
Diocetyl Phthalate	S		S	S	S			L	U	S		L	S	
Dioxane	U	U	S	U	L		U	U	U	L	U	U	S	L
Ethyl Acetate	L	U	S	L	L	S	U	U	U	S	U	U	S	L
Ethyl Alcohol (Ethanol)	S	U	S	S	S	S	S	S	L	S	S	L	S	S
Ethyl Chloride	U	L	U	U	L	S	U	S	U	S	U	L	S	L
Ethylamine	U	U	L	L								U	S	
Ethylene Bromide	L	U	L	U		S	U		U		U	U	S	
Ethylene Dichloride	U	U	L	U		S		S	U	S	U	L	S	L
Ethylene Glycol	S	U	S	S	S	S	S	S	S	S	S	L	S	S
Ferric Chloride	S	S	S	S	S	U	S	S	S	S	S	S	S	S
Fluorine (Gas)	U	U	U	U	L	S	S	L	U	U	L	L	S	U
Fluoroboric Acid	L	U	S	L				S	S	U		S	S	S
Fluorosilicic Acid	L		S	S		S	S	S	U	U	S	S	S	
Formaldehyde (40%)	S	U	S	S	S	S	S	L	S	S	S	S	S	L
Formic Acid (90%)	U	U	S	S	S	S	U	S	S	U	S	L	S	88% S
Freon 11 Refrigerant	S	U	L	S		S	U	S	S	U		S	L	
Freon 113 Refrigerant	S		L	U			S		S		S	S	L	
Freon 115 Refrigerant	S		L	U								S	L	
Freon 12 Refrigerant	S	L	L	S		S	S	S	S	S	U	L	L	
Freon 13 Refrigerant	S		S									S	L	
Freon 21 Refrigerant	S		S									U	S	
Freon 22 Refrigerant	S	U	S	L		S	U	S	S	S		U	S	
Freon 32 Refrigerant	S		S									U	L	
Furfural	S		L	U		S	U	L	U	S	U	U	S	L
Gasoline	S	U	L	U	L	S	U	S	S	S	S	S	S	U
Glycerol	S	S	S	S	S	S		S	S	S	S	S	S	S
Hexane	S	L	L	L	L		U	S	S	S	L	S	S	U
Hydrazine	L	L	S	U	U	S		S	U	U	U	U	S	S
Hydrobromic Acid (50%)	L	U	S	L	S	U	S	S	S	U	L	S	S	
Hydrochloric Acid (10%)	S	U	S	S	S	U	S	S	S	U	S	S	S	S
Hydrochloric Acid (36%)	U	U	S	S	S	U	S	S	S	U	U	S	S	Hot – U
Hydrofluoric Acid (40%)	U	U	S	S	S	S	L	S	S	U	U	S	S	U
Hydrogen Peroxide (35%)	U	U	S	L	S	S	S	S	S	To 5% L	S	S	S	S
Hydrogen Peroxide (87%)	U	U	S	U	S	S	S	L	S	U	S	S	S	
Hydrogen Sulphide (Gas)	S	L	S	S		S		S	S	L		S	S	S
Iso-Octane	S	U	S	U				S	S	S	S	S	S	U
Iso-Propyl Alcohol	S	L	S	S	S	S		S	L	U	S	S	S	S
Lactic Acid	S	S	S	S	S	S	U	L	S	S	S	S	S	S
Lead Acetate (10%)	S	U	S	S	S	S	S	S	S	S	S	L	S	S
Linseed Oil	S	L	S	S	S	S		S	S	S	S	S	S	L
Lubricating Oil	S	L	S	S		U		S	S	S	S	S	S	U
Magnesium Chloride	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Methyl Bromide	U	U	U	U		S	U	S	U	S		S	S	U
Methyl Ethyl Ketone	U	U	S	S	L	S	U	U	U	S	U	U	S	S
Methyl Alcohol (Methanol)	S	U	S	S	S	S	U	S	S	S	S	U	S	S

PO = Polyolefin in SuperPhobic Products
 PC = Polycarbonate
 PU = Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Methylene Dichloride	U	U	L	L		S						L	S	
Molasses	S	S	S	S		S	S	S	S	S		S	S	
Monoethanolamine	L	U	L	L				U	U	S		U	S	
N-Propyl Alcohol	S	U	S	S		L		S				S	S	S
Nickel Chloride	S	S	S	S	S	L	S	S	S	L	S	S	S	S
Nitric Acid (10%)	L	L		S	S	S	S	S	U	U	S	S	S	L
Nitric Acid (70%)	U	U	L	L	L	S	L	L	U	U	L	U	S	U
Nitrobenzene	U	U	L	L	L	S	U	L	U	S	U	L	S	U
Nitromethane	U	U	L	L	L	S	U	S	S	S	U	U	S	L
Nitropropane	L	U	L	L			U	U				U	S	L
Oleic Acid	S	L	S	S		S	U	S	L	L	S	S	S	U
Olive Oil	S	S	S	S		S	S	S	L	S	S	S	S	L
Oxalic Acid	S	L	S	S	S	S	S	L	S	S	S	S	S	S
Ozone (Gas)	L	L	L	U	S	S	S	S	S	U	S	S	S	S
Paraffin Oil	S	L	S	S	L	S	S	S	S	S	S	S	S	
Perchloroethylene	S	U	L	U	U	S	U	S	L	L	U	S	S	U
Peroxymono-sulphuric Acid	U	U			S	S						S		
Phenol	U	U	S	L	U	S	U	L	L	U	U	S	S	U
Phosphoric Acid (85%)	L	L	S	S	S	U	L	S	S	S	S	S	S	S
Picric Acid	U	U	S	U	S	S	S	L	U	L	U	S	S	L
Plating Solutions (<i>not chrome</i>)	L	L	S	S				S				S	S	S
Potassium Cyanide	S	S	S	S	S	S	S	S	S	S		S	S	S
Potassium Fluoride	S	S	S	S		S	S	S				S	S	
Potassium Hydroxide (50%)	S	U	S	S	S	S	S	U	S	L	U	L	S	S
Potassium Permanganate	U	U	S	S	S	S	S	S	S	U	S	S	S	
Potassium Sulphate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Propionic Acid	S	L	S	S	L		U	S	L	U	U	S	S	
Pyridine	U	U	L	S	L	S	U	U	U	L	U	U	S	L
Rapeseed Oil	L	L	L	U		S						S	S	S
Silicone Fluids	L	S	S	S	S	S	U	S	S	S	S	S	S	
Silver Nitrate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Borate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Carbonate	S	S	S	S	S	S	S	S	S	S	S	S	S	
Sodium Chloride	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Chlorite	S	S	S	S			S	S				S	S	
Sodium Cyanide	S	S	S	S	S	S	S	S	S	S		L	S	S
Sodium Hydroxide (10%)	S	U	S	S	S	S	S	L	S	S	S	L	S	S
Sodium Hydroxide (60%)	S	U	S	S	S	S	S	U	S	L	U	L	S	S
Sodium Hypochlorite (20%)	L	U	L	L	S	L	S	S	S	U	L	L	S	L
Sodium Nitrate	S	S	S	S	S	S	S	S	S	S	U	S	S	S
Sour Oil	S		L					L				L	S	U
Stannic Chloride	S	S	S	S		U		S	S	S	S	S	S	S
Styrene	L	U	L	L	L	S		S	U	S	U	S	S	U
Sulfamic Acid	L	U					S					L	S	
Sulphur Dioxide (Gas)	S	L	S	S	S	S	U	S	S	L	S	S	S	S
Sulphuric Acid (10%)	S	L	S	S	S	L	S	S	S	L	S	S	S	S
Sulphuric Acid (70%)	U	U	S	L	S	U	S	S	S	U	S	S	S	
Sulphuric Acid (96%)	U	U	S	L	L	U	S	S	U	U	U	L	S	U

PO = Polyolefin in SuperPhobic Products
PC = Polycarbonate
PU = Polyurethane

PE = Polyethylene
PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Sulphuric Acid (Fuming)	U	U	L	U	U	U		U	U	U	U	L	S	
Tetrachloroethane	S	U	L	L		S	U	S	L	L		S	S	U
Tetrahydrofurane	U	U	L	L	L	S	U	U	U	S	U	U	S	L
Tetrahydro-naphthalene	S	U	L	U								S	S	
Thionyl Chloride	U		U	U	U		U	U	U	U	U	U	S	L
Titanium Tetrachloride	S	S	L	L				S				S	S	U
Toluene	L	U	L	U	L	S	U	S	U	S	U	S	S	U
Transformer Oil	S	S	S	L			S					S	S	U
Trichloroacetic Acid	L	U	S	S	S	L		L	L	L	U	L	S	L
Trichloroethane	L	U	U	U	U	S	U	S	L	L	U	S	S	U
Trichloroethylene	L	U	U	U	U	S	U	S	U	L	U	L	S	U
Tricresyl Phosphate	S		S	S		S	U	U	U	S		S		S
Triethanolamine	S	U	S	L				L				U	S	L
Triethylamine	S	U	S	U		S	U	L	S	S		L	S	
Turpentine	L	U	L	L	L	S	U	S	U	S	U	S	S	U
Vegetable Oils	S	S	L	L		S	S	S	S	S		S	S	L
Vinyl Acetate	L	L	S	S		S	U	S	U			U	S	L
Vinyl Chloride	U	L	U			S	U	S	U	S		S	S	U
Water (Distilled)	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Water (Sea)	S	S	S	S	S	S		S	S	S	S	S	S	
Wine	S	U	S	S		S	L	S	S	S	S	S	S	S
Xylene	L	U	L	U	L	S	U	S	U	S	U	S	S	U

PO = Polyolefin in SuperPhobic Products
 PC = Polycarbonate
 PU = Polyurethane

PE = Polyethylene
 PP = Polypropylene

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M, Membrana, Liqui-Cel, SuperPhobic, MiniModule and MicroModule are trademarks of 3M Company. All other trademarks are the property of their respective owners.

© 2015 3M Company. All rights reserved. Chemical GD_Rev6



**Industrial Business Group
 Membranes Business Unit**
 13840 South Lakes Drive
 Charlotte, North Carolina 28273
 USA

Phone: +1 704 587 8888
 Fax: +1 704 587 8610

**3M Deutschland GmbH
 Membranes Business Unit**
 Önder Straße 28
 42289 Wuppertal
 Germany

Phone: +49 202 6099 - 658
 Fax: +49 202 6099 - 750

**3M Japan Ltd.
 Membranes Business Unit**
 6-7-29, Kita-Shinagawa,
 Shinagawa-ku, Tokyo | 141-8684
 Japan

Phone: +81 3 6409 5732
 Fax: +81 3 6409 5827

MEMBRANA
 Now proudly part of 3M

www.liqui-cel.com

